



## Product Specifications

# Mitchell Collection - MELLOW



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	20.0 oz/yd	ASTM D 751-06
Thickness	1.1 mm $\pm$ 10%	ASTM D 751-06
Total Weight	13.3 oz./yd <sup>2</sup> $\pm$ 10%	ASTM D 751-06
Backing Composition	65% Polyester/35% Cotton	ASTM D 751-06
Backing Weight	6.0 oz / yd <sup>2</sup>	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

  

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	100 lbs./in. x 150 lbs./in. min.	ASTM D 751-06
Trap Tear	20 lbs./in. x 25 lbs./in. min.	ASTM D 751-06
Seam Strength	85 lbs./in. x 100 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	2% x 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	Pass - No Blocking	FTMS 19 - M5872
Cold Crack	Pass - No Cracking or Flaking	FTMS 19 - M5874
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	15,000 cycles, #10 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	3 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

  

<u>Flammability</u>	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Suitable Applications: Residential

Country of Origin: China

05/09/2017 - Revision: 3