



Product Specifications

Mitchell Collection - ALLIE



Technical

<u>Technical</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	31.5 oz/yd	ASTM D 751-06
Thickness	1.1 mm \pm 10%	ASTM D 751-06
Total Weight	21 oz./yd ² \pm 10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	4.7 oz / yd ²	ASTM D 751-06
Repeat	V: 21"/ H: 20"	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	85 lbs./in. x 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15 lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. x 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	2% x 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
UV Stability	40 hours (no color change)	ASTM D 4329-05
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	30,000 cycles, wire screen	ASTM D 4157-92

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

7p Free - Does not contains the following phthalates: DBP, BBP, DEHP, DOP, DNOP, DINP, DIDP

Suitable Applications: Residential

Country of Origin: China

01/27/2016 - Revision: 3