



Product Specifications

Mitchell Collection - BARRINGTON



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	19.5 oz/yd	ASTM D 751-06
Thickness	1.0 mm $\pm 10\%$	ASTM D 751-06
Total Weight	13 oz./yd ² $\pm 10\%$	ASTM D 751-06
Backing Composition	80% Polyester / 20% Cotton	ASTM D 751-06
Backing Weight	6.8 oz / yd ² $\pm 10\%$	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 80 lbs./in. min.	ASTM D 751-06
Trap Tear	40 lbs./in. x 40 lbs./in. min.	ASTM D 751-06
Seam Strength	50 lbs./in. x 50 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	2% x 8%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Hydrolysis Resistance	7 weeks - No delamination	ASTM D 3690-02
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	120 hours (no color change)	ASTM D 4329-05

Flammability

California Bulletin 117-2013, Section 1	Pass
MVSS #302	Pass
NFPA 260	Pass

Suitable Applications: Commercial

Country of Origin: China

10/31/2014 - Revision: 1