



Product Specifications

Mitchell Collection - BUCKEYE



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	24 oz/yd	ASTM D 751-06
Thickness	1.0 mm \pm 10%	ASTM D 751-06
Total Weight	22.0 oz./yd ² \pm 10%	ASTM D 751-06
Backing Composition	65% Polyester/35% Cotton	ASTM D 751-06
Backing Weight	3.5 oz / yd ²	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 85 lbs./in. min.	ASTM D 751-06
Trap Tear	12 lbs./in. x 12 lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. x 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	2% x 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	50,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	40 hours	ASTM D 4329-05

<u>Flammability</u>	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass
MVSS/CMVSS	Pass

Suitable Applications: Residential

Country of Origin: China

02/09/2015 - Revision: 2