



Product Specifications

Mitchell Collection - COLORADO



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	Polyester	
Finished Width	54" min.	ASTM D 751-06
Weight at 55 inches	15.5 oz/yd	ASTM D 751-06
Thickness	1.0 mm $\pm 10\%$	ASTM D 751-06
Total Weight	10.1 oz./yd ² $\pm 10\%$	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	6.4 oz./yd ² $\pm 10\%$	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	50 yards	
Cleaning Code	W	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	150 lbs./in. \times 150 lbs./in. min.	ASTM D 751-06
Trap Tear	10 lbs./in. \times 9 lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. \times 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. \times 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD \times CD)	2% \times 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crocking Resistance	Dry - 4 ; Wet - 4	AATCC 8-2007
Wyzenbeek Abrasion	90,000 cycles; #10 Cotton Duck	ASTM D 4157-10
UV Stability	40 hours (2-3, some color change)	ASTM D 4329-05

<u>Flammability</u>	
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Suitable Applications: Residential

Country of Origin: China

11/25/2014 - Revision: 1