



Product Specifications

Mitchell Collection - IMAGINE



Technical

| | <u>Values</u> | <u>Test Method</u> |
|---------------------|------------------------------------|--------------------|
| Surface Composition | PVC | |
| Finished Width | 54" min. | ASTM D 751-06 |
| Weight at 54 inches | 33.0 oz/yd | ASTM D 751-06 |
| Thickness | 1.0 mm \pm 10% | ASTM D 751-06 |
| Total Weight | 22.0 oz./yd ² \pm 10% | ASTM D 751-06 |
| Backing Composition | 70% Polyester / 30% Cotton | ASTM D 751-06 |
| Backing Weight | 3.5 oz / yd ² | ASTM D 751-06 |
| Repeat | None | |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | W | |

Performance

| | <u>Values</u> | <u>Test Method</u> |
|-------------------------|---------------------------------|----------------------|
| Grab Tensile | 85 lbs./in. x 90 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 15 lbs./in. x 15lbs./in. min. | ASTM D 751-06 |
| Seam Strength | 65 lbs./in. x 65 lbs./in. min. | ASTM D 751-06 |
| Adhesion | 4 lbs./in. x 4 lbs./in. min. | ASTM D 751-06 |
| Stretch @ 15# (MD x CD) | 2% x 9% | ASTM D 751-06 |
| Flex Resistance | 25,000 Cycles | ASTM D 2097-03(2010) |
| Blocking | No. 1 - Pass | FTMS 191A-TM5872 |
| Crock Resistance | 20 cycles - Pass | AATCC 8-2007 |
| Wyzenbeek Abrasion | 100,000 cycles, #10 cotton duck | ASTM D 4157-92 |
| UV Stability | 40 hours (no color change) | ASTM D 4329-05 |

Flammability

| |
|---|
| California Bulletin 117-2013, Section 1 |
| U.F.A.C. Class I |
| NFPA 260 |

Values

| |
|------|
| Pass |
| Pass |
| Pass |

Environmental

7p Free - Does not contains the following phthalates: DBP, BBP, DEHP, DOP, DNOP, DINP, DIDP

Suitable Applications: Commercial

Country of Origin: China

01/27/2016 - Revision: 3