



Product Specifications

Mitchell Collection - LEXI



Technical Specs

<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	20 oz/yd ±10%	ASTM D 751-06
Thickness	1.0 mm ±10%	ASTM D 751-06
Total Weight	13.3 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	6.8 oz / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	50 lbs./in. × 50 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18lbs./in. min.	ASTM D 751-06
Seam Strength	40 lbs./in. × 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	10% × 20%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	7 weeks	ISO 1419: 1995 E
	7 weeks	ASTM D 3690-02
Lightfastness	150 hours	ASTM D 4329-05

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass
IMO A.652(16) Section 8.2	Pass
FMVSS/CMVSS #302	Pass

Environmental

- 1.No PVC or Phthalates
2. No persistent organic pollutants
3. No toxic by-products
4. No flame retardant chemicals
5. RoHS and REACH compliant
6. Over 99% of solvents recaptured and recycled

Suitable Applications: Commercial; Residential

Country of Origin: China

09/25/2017 - Revision: 11