



## Product Specifications

# Mitchell Collection - LONDON



| <u>Technical Specs</u>                  | <u>Values</u>                      | <u>Test Method</u>   |
|---|------------------------------------|----------------------|
| Surface Composition                     | 100% PVC                           |                      |
| Finished Width                          | 54" min.                           | ASTM D 751-06        |
| Weight at 54 inches                     | 33 oz/yd                           | ASTM D 751-06        |
| Thickness                               | 1.1 mm $\pm$ 10%                   | ASTM D 751-06        |
| Total Weight                            | 22 oz./yd <sup>2</sup> $\pm$ 10%   | ASTM D 751-06        |
| Backing Composition                     | 65% Polyester / 35% Cotton         | ASTM D 751-06        |
| Backing Weight                          | 3.5 oz / yd <sup>2</sup> $\pm$ 10% | ASTM D 751-06        |
| Repeat                                  | None                               |                      |
| Railroaded                              | No                                 |                      |
| Put-up                                  | 30 yards                           |                      |
| Cleaning Code                           | W                                  |                      |
| <br>                                    |                                    |                      |
| <u>Performance</u>                      | <u>Values</u>                      | <u>Test Method</u>   |
| Grab Tensile                            | 85 lbs./in. x 90 lbs./in. min.     | ASTM D 751-06        |
| Trap Tear                               | 15 lbs./in. x 15 lbs./in. min.     | ASTM D 751-06        |
| Seam Strength                           | 65 lbs./in. x 65 lbs./in. min.     | ASTM D 751-06        |
| Adhesion                                | 4 lbs./in. x 4 lbs./in. min.       | ASTM D 751-06        |
| Stretch @ 15# (MD x CD)                 | 2% x 9%                            | ASTM D 751-06        |
| Flex Resistance                         | 25,000 Cycles                      | ASTM D 2097-03(2010) |
| Blocking                                | No. 1 - Pass                       | FTMS 191A-TM5872     |
| Crock Resistance                        | Wet-4; Dry-4                       | AATCC 8-2007         |
| Wyzenbeek Abrasion                      | 100,000 cycles, wire screen        | ASTM D 4157-92       |
| UV Stability                            | 40 hours                           | ASTM D 4329-05       |
| <br>                                    |                                    |                      |
| <u>Flammability</u>                     |                                    |                      |
| California Bulletin 117-2013, Section 1 | Pass                               |                      |
| U.F.A.C. Class I                        | Pass                               |                      |
| NFPA 260                                | Pass                               |                      |

**Suitable Applications:** Commercial

**Country of Origin:** China

**11/11/2014 - Revision: 1**