



Product Specifications

Mitchell Collection - LUXURY



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PU	
Finished Width	54" min.	ASTM D 751-89
Weight at 54 inches	25.5 oz/yd	ASTM D 751-89
Thickness	2.5 mm \pm 10%	ASTM D 751-89
Total Weight	16.7 oz./yd ² \pm 10%	ASTM D 751-89
Backing Composition	100% Polyester	ASTM D 751-89
Backing Weight	5.7 oz / yd ²	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	30-50 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	150 lbs./in. \times 100 lbs./in. min.	ASTM D 5034-09
Trap Tear	20 lbs./in. \times 20 lbs./in. min.	ASTM D 5587-07
Seam Strength	70 lbs./in. \times 60 lbs./in. min.	ASTM D 1683-11A
Adhesion	4 lbs./in. \times 4 lbs./in. min.	ASTM D 751-89
Stretch at 15# MD (warp) \times CD (fill)	2 % \times 9%	ASTM D 751-89
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Hydolysis Resistance	3 weeks	ISO 5423: 1992 E
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-13
UV Stability	40 hours	AATCC 16-2004
Crocking Resistance	Wet-4; Dry-4	AATCC 8-2007
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
U.F.A.C. Class I	Pass	
NFPA 260	Pass	

Suitable Applications: Residential

Country of Origin: China

04/11/2017 - Revision 4