



## Product Specifications

# Mitchell Collection - MAGIC



### Technical Specs

<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Top Finish	Polyurethane - 5%	ASTM D 751-06
Surface Composition	PVC Foam - 70%	ASTM D 751-06
Backing Composition	Polyester - 25%	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	31 oz./yd. ±10%	ASTM D 751-06
Thickness	1.1 mm ±10%	ASTM D 751-06
Total Weight	21 oz./yd <sup>2</sup> ±10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	5.3 oz. / yd <sup>2</sup>	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

### Performance

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18 lbs./in. min.	ASTM D 751-06
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	80,000 cycles, #10 cotton duck	ASTM D 4157-13
Hydrolysis Resistance	5 weeks	ISO 5423: 1992E
UV Stability	150 hours	ASTM D 4329-05
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Stretch (MD×CD)	2% × 6% at 15 lbs.	ASTM D 751-06

### Flammability

California Bulletin 117-2013, Section 1 Pass

### Environmental

Does not contain any flame retardant chemicals.

### Cleaning

**Suitable Applications:** Hospitality

Do not use chemical cleaners.  
Mild soap and water only.

**Country of Origin:** China

**03/19/2018 - Revision: 4**