



Product Specifications

Mitchell Collection - MISSISSIPPI



<u>Technical</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	27.0 oz/yd	ASTM D 751-06
Thickness	1.0 mm \pm 10%	ASTM D 751-06
Total Weight	18.0 oz./yd ² \pm 10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	3.5 oz / yd ²	ASTM D 751-06
Repeat	V: 11.5"; H: 9.0"	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	85 lbs./in. x 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. x 15lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. x 65 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MDxCD)	2% x 9%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
UV Stability	40 hours	ASTM D 4329-05
<u>Flammability</u>	<u>Values</u>	<u>Environmental</u>
California Bulletin 117-2013, Section 1	Pass	7p Free - Does not contains the
U.F.A.C. Class I	Pass	following phthalates: DBP, BBP,
NFPA 260	Pass	DEHP, DOP, DNOP, DINP, DIDP
CMVSS#302	Pass	

Suitable Applications: Commercial

Country of Origin: China

01/27/2016 - Revision: 5