



Product Specifications

Mitchell Collection - OUTBACK



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PU	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	22.5 oz/yd	ASTM D 751-06
Thickness	1.0 mm \pm 10%	ASTM D 751-06
Total Weight	15 oz./yd ² \pm 10%	ASTM D 751-06
Backing Composition	65% Polyester / 35% Cotton	ASTM D 751-06
Backing Weight	4.0 oz / yd ² \pm 10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 - 50 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 70 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. x 12 lbs./in. min.	ASTM D 2261-11
Seam Strength	60 lbs./in. x 60 lbs./in. min.	ASTM D 1683-11a
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	2% x 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
Hydrolysis Resistance	7 weeks	ISO 1419: 1995 E
UV Stability	150 hours	ASTM D 4329-05

Flammability

	<u>Values</u>
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

- 1.No PVC or Phthalates
2. No persistent organic pollutants
3. No toxic by-products
4. No flame retardant chemicals
5. RoHS and REACH compliant
6. Over 99% of solvents recaptured and recycled

Suitable Applications: Commercial; Residential

Country of Origin: China

01/16/2018 - Revision: 6