



Product Specifications

Mitchell Collection: PACIFIC



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	PVC	
Finished Width	54" min.	ASTM D 751-89
Weight at 54 inches	33.3 oz./yd. \pm 10%	ASTM D 751-89
Thickness	1.2 mm \pm 10%	ASTM D 751-89
Total Weight	20.2 oz./yd ² \pm 10%	ASTM D 751-89
Backing Composition	100% Polyester	ASTM D 751-89
Backing Weight	3.1 oz. / yd ² \pm 10%	ASTM D 751-89
Put-up	30 yards	
Repeat	None	
Railroaded	No	
Cleaning Code	W/S	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. \times 100 lbs./in. minimum	ASTM D 751-89
Trap Tear	20 lbs./in. \times 20 lbs./in. minimum	ASTM D 751-89
Seam Strength	50 lbs./in. \times 50 lbs./in. minimum	ASTM D 751-89
Adhesion	4 lbs./in. \times 4 lbs./in. minimum	ASTM D 751-89
Stretch at 15# MD (warp) \times CD (fill)	4% \times 12%	ASTM D 751-89
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-07
UV Stability	650 hours	ASTM D 4329-05
Mildew Resistance	Pass - No Growth	ASTM G-21
Crock Resistance	Wet - Class 4; Dry - Class 4	AATCC 8-2007
Pink Stain	Pass	ASTM E 1428
Cold Crack (Roller Method)	Pass -40°F	CFFA-6a
<u>Flammability</u>		
California Bulletin 117-2013, Section 1	Pass	
MVSS #302	Pass	
IMO A.652(16) 8.2 & 8.3	Pass	

Suitable Applications: Commercial; Outdoor/Marine

Country of Origin: China

03/21/2017 - Revision: 2