



Product Specifications

Mitchell Collection - SOUTH PARK



<u>Technical</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	30.0 oz/yd	ASTM D 751-06
Thickness	1.4 mm \pm 10%	ASTM D 751-06
Total Weight	20 oz./yd ² \pm 10%	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Backing Weight	3.5 oz /yd ²	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	85 lbs./in. x 75 lbs./in. min.	ASTM D 751-06
Trap Tear	20 lbs./in. x 20 lbs./in. min.	ASTM D 751-06
Seam Strength	35 lbs./in. x 30 lbs./in. min.	ASTM D 751-06
Adhesion	3 lbs./in. x 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD x CD)	8% x 18%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	35,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	40 hours (no color change)	ASTM D 4329-05

<u>Flammability</u>	<u>Values</u>
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass
CMVSS #302	Pass

Suitable Applications: Residential; RV

Country of Origin: China

012/11/2014 - Revision: 3