



Product Specifications

ReCast® - APACHE



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	33 oz/yd	ASTM D 751-06
Thickness	1.2 mm ±10%	ASTM D 751-06
Total Weight	22 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	60% leather / 40% polyester	ASTM D 751-06
Backing Weight	6.4 oz / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	90 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Trap Tear	12 lbs./in. × 12 lbs./in. min.	ASTM D 5733-99
Seam Strength	50 lbs./in. × 50 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) ×CD (fill)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2005
Wyzenbeek Abrasion	Pass 100,000 cycles, #8 Cotton Duck	ASTM D 4157-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260 Class 1	Pass

Suitable Applications: Residential

Country of Origin: China

12/08/2014 - Revision: 5