



Product Specifications

ReCast® - SONORAN



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	22 oz./yd.	ASTM D 751-06
Thickness	1.2 mm ±10%	ASTM D 751-06
Total Weight	14.7 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	60% Leather / 40% Polyester	ASTM D 751-06
Backing Weight	8.0 oz./yd ²	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) × CD (fill)	2% × 7%	ASTM D 751-06
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2005
Wyzenbeek Abrasion	Pass 100,000 cycles, #10 Cotton Duck	ASTM D 4157-02
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	40 hours (no color change)	ASTM D 4329-05

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260 Class 1	Pass

Suitable Applications: Commercial; Residential

Country of Origin: China

12/31/2015 - Revision: 4