



Product Specifications

ReCast® - TUSCANY



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	Polyurethane/PVC	
Finished Width	54" min.	ASTM D 751-06
Weight at 54 inches	31.0 oz./yd.	ASTM D 751-06
Thickness	1.2 mm ±10%	ASTM D 751-06
Total Weight	23.0 oz./yd ² ±10%	ASTM D 751-06
Backing Composition	60% Polyester / 40% Leather	ASTM D 751-06
Backing Weight	4.8 oz. / yd ² ±10%	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	50 lbs./in. × 50 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5733-99
Seam Strength	40 lbs./in. × 40 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch at 15# MD (warp) ×CD (fill)	10% ×15%	ASTM D 751-06
Blocking	No. 1 - Pass	Fed. Std. 191 A, 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2005
Wyzenbeek Abrasion	Pass 50,000 cycles, #10 Cotton Duck	ASTM D 4157-02
Hydrolysis Resistance	5 weeks	ASTM D 3690-02
UV Stability	150 hours	ASTM D 4329-05

Flammability

California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260 Class 1	Pass

Suitable Applications: Commercial, Residential

Country of Origin: China

12/02/2016 - Revision: 6