



Product Specifications

Sta-Kleen® - CAMO

sta-kleen®
PERFORMANCE FABRIC

Technical Specs

	<u>Values</u>
Surface Composition	100% PU
Finished Width	54" min.
Weight at 54 inches	21 oz./yd.
Thickness	1.0 mm ±10%
Total Weight	14 oz./yd ² ±10%
Backing Composition	65% Polyester / 35% Cotton
Backing Weight	3.5 oz. / yd ²
Put-up	30 yards
Repeat	None
Railroaded	No
Cleaning Code	W/S

Test Method

ASTM D 751-89
ASTM D 751-89
ASTM D 751-89
ASTM D 751-89
ASTM D 751-89
ASTM D 751-89

Performance

	<u>Values</u>
Grab Tensile	80 lbs./in. × 70 lbs./in. min.
Trap Tear	15 lbs./in. × 15 lbs./in. min.
Seam Strength	60 lbs./in. × 60 lbs./in. min.
Adhesion	4 lbs./in. × 4 lbs./in. min.
Stretch at 15# MD (warp) × CD (fill)	2% × 7%
Flex Resistance	50,000 cycles
Blocking	No. 1 - Pass
Crock Resistance	Dry-4; Wet-4
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck
Hydrolysis Resistance	7 weeks
UV Stability	150 hours
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5
Anti-Bacterial	Pass
Mildew Resistance	Pass

Test Method

ASTM D 5034-09
ASTM D 5587-07
ASTM D 1683-07A
ASTM D 751-89
ASTM D 751-89
ASTM D 2097-03
Fed. Std. 191 A , 5872
AATCC 8
ASTM D 4157-07
ISO 1419: 1995 E
ASTM D 4329
LP-463KC-04-03
AATCC 147-2004
ASTM G-21

Flammability

IMO A.652(16)8.2	Pass
California Bulletin 117-2013, Section 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

Does not contain PFAS, PFOA or formaldehyde.



A PRACTICE GREENHEALTH PROGRAM

Suitable Applications: Hospitality, Contract, Healthcare, Residential

Country of Origin: China

11/01/2016 - Revision: 7