



Product Specifications

Sta-Kleen® - CRATER



Technical Specs

	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-89
Weight at 54 inches	21.0 oz/yd	ASTM D 751-89
Thickness	1.0 mm ±10%	ASTM D 751-89
Total Weight	13.6 oz./yd ² ±10%	ASTM D 751-89
Backing Composition	100% Polyester	ASTM D 751-89
Backing Weight	4.0 oz/yd ²	ASTM D 751-89
Put-up	30 yards	
Repeat	None	
Railroaded	No	
Cleaning Code	W/S	

Performance

	<u>Values</u>	<u>Test Method</u>
Grab Tensile	90 lbs./in. × 80 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 1683-07A
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-89
Stretch at 15# MD (warp) × CD (fill)	2% × 12%	ASTM D 751-89
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-07
Hydrolysis Resistance	7 weeks	ISO 1419: 1995 E
UV Stability	150 hours	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03
Anti-Bacterial	Pass	AATCC 147-2004
Mildew Resistance	Pass	ASTM G-21

Flammability

IMO A.652(16)8.2	Pass
California Technical Bulletin 117-2013, Sec. 1	Pass
U.F.A.C. Class I	Pass
NFPA 260	Pass

Environmental

Does not contain PFAS,
PFOA or formaldehyde.

Suitable Applications: Hospitality, Contract, Healthcare, Residential

Country of Origin: China

11/11/2016 - Revision: 9

