



Product Specifications

Sta-Kleen® - SCORE



<u>Technical Specs</u>	<u>Values</u>	<u>Test Method</u>
Surface Composition	100% Polyurethane	
Finished Width	54" min.	ASTM D 751-89
Weight at 54 inches	21.0 oz/yd	ASTM D 751-89
Thickness	1.0 mm ±10%	ASTM D 751-89
Total Weight	14.0 oz./yd ² ±10%	ASTM D 751-89
Backing Composition	85% Polyester / 15% Cotton	ASTM D 751-89
Backing Weight	4.9 oz / yd ² ±10%	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W/S	
<u>Performance</u>	<u>Values</u>	<u>Test Method</u>
Grab Tensile	80 lbs./in. x 80 lbs./in. min.	ASTM D 5034-09
Trap Tear	15 lbs./in. x 15 lbs./in. min.	ASTM D 5587-07
Seam Strength	45 lbs./in. x 35 lbs./in. min.	ASTM D 1683-07A
Adhesion	4 lbs./in. x 4 lbs./in. min.	ASTM D 3690-02
Stretch at 15# MD (warp) xCD (fill)	2% x 6%	ASTM D 751-89
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872
Crock Resistance	Dry-4; Wet-4	AATCC 8
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	ASTM D 4157-07
Hydrolysis Resistance	7 weeks	ISO 1419: 1995 E
UV Stability	150 hours	ASTM D 4329-05
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5	LP-463KC-04-03
Anti-Bacterial	Pass	AATCC 147-2004
Mildew Resistance	Pass	ASTM G-21
<u>Flammability</u>		<u>Environmental</u>
IMO A.652(16)8.2	Pass	Does not contain PFAS,
California Bulletin 117-2013, Section 1	Pass	PFOA or formaldehyde.
U.F.A.C. Class I	Pass	
NFPA 260	Pass	

Suitable Applications: Hospitality, Contract, Healthcare, Residential

Country of Origin: China



11/11/2016 - Revision: 9