



Product Specifications

Sta-Kleen - TIP TOP



| <u>Technical Specs</u> | <u>Values</u> | <u>Test Method</u> |
|---|--|--|
| Surface Composition | 100% Polyurethane | |
| Finished Width | 54" min. | ASTM D 751-89 |
| Weight at 54 inches | 24.3 oz./yd. | ASTM D 751-89 |
| Thickness | 1.1 mm ±10% | ASTM D 751-89 |
| Total Weight | 16.1 oz./yd ² ±10% | ASTM D 751-89 |
| Backing Composition | 46% Polyester / 24% Cotton / 30% Leather | ASTM D 751-89 |
| Backing Weight | 9.2 oz. / yd ² | ASTM D 751-89 |
| Repeat | None | |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | W/S | |
| | | |
| <u>Performance</u> | <u>Values</u> | <u>Test Method</u> |
| Grab Tensile | 100 lbs./in. x 80 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 18 lbs./in. x 15 lbs./in. min. | ASTM D 5733-99 |
| Seam Strength | 65 lbs./in. x 65 lbs./in. | ASTM D 751-06 |
| Adhesion | 4 lbs./in. x 4 lbs./in. min. | ASTM D 751-06 |
| Stretch @15# MD (warp) x CD (fill) | 2% x 7% | ASTM D 751-89 |
| Flex Resistance | 25,000 cycles | ASTM D 2097-03-02 |
| Blocking | No. 1 Pass | Fed. Std. 191 A , 5872 |
| Crock Resistance | Dry-4; Wet-4 | AATCC 8 |
| Wyzenbeek Abrasion | 100,000 cycles, #10 Cotton Duck | ASTM D 4157-02 |
| Hydrolysis Resistance | 7 weeks | ISO 1419: 1995 E |
| UV Stability | 150 hours | ASTM D 4329 |
| Blue Dye Transfer Resistance | Dry-4-5; Wet-4-5 | LP-463KC-04-03 |
| Anti-Bacterial | Pass | AATCC 147-2004 |
| Mildew Resistance | Pass | ASTM G-21 |
| | | |
| <u>Flammability</u> | | <u>Environmental</u> |
| California Bulletin 117-2013, Section 1 | Pass | Does not contain PFAS, PFOA or formaldehyde. |
| U.F.A.C. Class I | Pass | |
| NFPA 260 | Pass | |
| FMVSS 302 | Pass | |
| IMO A.652(16)8.2 | Pass | |



Suitable Applications: Hospitality, Contact, Healthcare, Residential

Country of Origin: China

11/11/2016 - Revision: 7