



Product Specifications

Sta-Kleen® - TUCSON



Technical Specs

Technical Specs	Values
Surface Composition	100% Polyurethane
Finished Width	54" min.
Weight at 54 inches	22.4 oz./yd. ±10%
Thickness	1.0 mm ±10%
Total Weight	16.2 oz./yd ² ±10%
Backing Composition	85% Polyester/15% Cotton
Backing Weight	4.9 oz. / yd ² ±10%
Repeat	None
Railroaded	No
Put-up	30 yards
Cleaning Code	W/S

Test Method

ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06

Performance

Performance	Values
Grab Tensile	80 lbs./in. x 80 lbs./in. min.
Trap Tear	15 lbs./in. x 15 lbs./in. min.
Seam Strength	40 lbs./in. x 40 lbs./in. min.
Adhesion	4 lbs./in. x 4 lbs./in. min.
Stretch at 15# MD (warp) xCD (fill)	2% x 7%
Flex Resistance	25,000 cycles
Blocking	No. 1 - Pass
Crock Resistance	Dry-4; Wet-4
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck
Hydrolysis Resistance	10 weeks
	10 weeks
Colorfastness to Light	200 hours
Blue Dye Transfer Resistance	Dry-4-5; Wet-4-5
Anti-Bacterial	Pass
Mildew Resistance	Pass
Cold Crack (#5 roller)	-20°F

Test Method

ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 751-06
ASTM D 2097-91
Fed. Std. 191 A , 5872
AATCC 8-2007
ASTM D 4157-07
ASTM D 3690-02
ISO 1419: 1995
ASTM D 4329-05
LP-463KC-04-03
AATCC 147-2004
ASTM G-21
CFFA-6A

Flammability

California Bulletin 117-2013, Section 1	Pass
NFPA 260	Pass
UFAC Class I	Pass
IMO A.652(16)8.2	Pass



Environmental

Does not contain PFAS, PFOA or formaldehyde. Does not contain chemical flame retardants. RoHS and REACH compliant.

Suitable Applications: Hospitality, Contract, Healthcare, Residential

Country of Origin: China

11/15/2017 - Revision: 4