



Aloe



Chocolate



Grey



Saddle Brown



Smoke

| Construction | Values | Test Method |
|---------------------|-------------------|---------------|
| Surface Composition | 100% Polyurethane | |
| Backing Composition | 100% Polyester | ASTM D 751-89 |
| Finished Width | 54" min. | ASTM D 751-89 |
| Repeat | None | |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | W | |

| Performance | Values | Test Method |
|-----------------------|----------------------------------|-----------------------|
| Grab Tensile | 100 lbs./in. × 100 lbs./in. min. | ASTM D 5034-09 |
| Trap Tear | 15 lbs./in. × 15 lbs./in. min. | ASTM D 5587-07 |
| Seam Strength | 35 lbs./in. × 35 lbs./in. min. | ASTM D 1683-07A |
| Adhesion | 3 lbs./in. × 3 lbs./in. min. | ASTM D 751-89 |
| Stretch @ 15# (MD×CD) | 2% × 2% | ASTM D 751-89 |
| Flex Resistance | 25,000 Cycles | ASTM D 2097-91 |
| Blocking | No. 1 - Pass | Fed. Std. 191 A, 5872 |
| Crock Resistance | D-4; W-4 | Fed. Std. 191 A, 5651 |
| Wyzenbeek Abrasion | 25,000 cycles, #10 cotton duck | ASTM D 4157-07 |
| Hydrolysis Resistance | 3 weeks | ISO 5423: 1992 E |
| UV Stability | 40 hours (Grade 4) | AATCC 16-2004 |

| Flammability | Environmental |
|--|---|
| California Technical Bulletin 117-2013, Sec. 1 | Pass 1. No anti-microbial additives |
| FMVSS & CMVSS 302 | Pass 2. Does not contain PFAS, PFOA |
| NFPA 260 | Pass 3. Prop 65 compliant |
| U.F.A.C. Class I | Pass 4. No chemical flame retardants, CA AB2998 compliant |
| | 5. REACH, RoHS, and LEED compliant |

Suitable Applications Residential, RV

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.