









Construction	Values	Test Method	
Surface Composition	PVC	ASTM D 751-06	
Finished Width	54" min.	ASTM D 751-06	
Backing Composition	100% Polyester	ASTM D 751-06	
Repeat	None	ASTM D 751-06	
Railroaded	No		
Put-up	30 yards		
Cleaning Code	W/S		
Performance	Values	Test Method	
Grab Tensile	110 lbs./in.× 110 lbs./in. min.	ASTM D 751-06	
Trap Tear	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06	
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06	
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06	
Stretch @ 15# (MD×CD)	7% × 30%	ASTM D 751-06	
Flex Resistance	25,000 Cycles	ASTM D 2097-91	
Blocking	No. 1 - Pass	FTMS 191A-TM5872	
Crock Resistance	Dry - 4-5; Wet - 4-5	AATCC 8-2016	
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13	
Colorfastness to Light	200 hours, Grade 4-5	ASTM D 4329-05	
Blue Dye Transfer Resistance	Dry - 4-5; Wet - 4	Chrysler Method: LP-463KC-04-03	
Flammability	Environmento	al	
California Technical Bulletin 117-2	2013, Sec. 1 Pass 1. No anti-mic	robial additives	

			Environmental
California Technical Bulletir	n 117-2013, Sec. 1	Pass	1. No anti-microbial additives
FMVSS/CMVSS #302		Pass	2. Does not contain PFAS, PFOA
IMO A.652(16)8.2		Pass	3. Prop 65 compliant
NFPA 260		Pass	4. No chemical flame retardants, CA AB2998 compliant
U.F.A.C. Class I		Pass	5. RoHS compliant – Phthalate free

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

