







Construction

## **Product Specifications**

**Values** 

**Test Method** 

FTMS 191A-TM5872

**AATCC 8-2016** 

ASTM D 4157-13

ASTM D 4329-05

Chrysler Method: LP-463KC-04-03



Surface Composition	PVC	ASTM D 751-06		
Finished Width	54" min.	ASTM D 751-06		
Backing Composition	100% Polyester	ASTM D 751-06		
Repeat	None	ASTM D 751-06		
Railroaded	No			
Put-up	30 yards			
Cleaning Code	W/S			
Performance	Values	Test Method		
Grab Tensile	110 lbs./in.× 110 lbs./in. min.	ASTM D 751-06		
Trap Tear	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06		
Seam Strength	35 lbs./in. × 35 lbs./in. min.	ASTM D 751-06		
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06		
Stretch @ 15# (MD×CD)	7% × 30%	ASTM D 751-06		
,	7/0 ^ 30/0	A311VI D 731-00		

			lity

Crock Resistance

Wyzenbeek Abrasion

Colorfastness to Light

Blue Dye Transfer Resistance

Blocking

Flammability		Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
FMVSS/CMVSS #302	Pass	2. Does not contain PFAS, PFOA
IMO A.652(16)8.2	Pass	3. Prop 65 compliant
NFPA 260	Pass	4. No chemical flame retardants, CA AB2998 compliant
U.F.A.C. Class I	Pass	5. RoHS compliant – Phthalate free

No. 1 - Pass

Dry - 4-5; Wet - 4-5

Dry - 4-5; Wet - 4

200 hours, Grade 4-5

100,000 cycles, #10 cotton duck

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



