

Abyss



Atlantic




Cadet




Camel



Chia




Chocolate



Cream



Flax



Fox



Iron




Lingonberry



Ocean




Pacific



Pear




Pebble



Pecan




Plum




Poppy




Rain



Reef



Rust



Sage



Spruce



Walnut

| Construction        | Values         | Test Method   |
|---------------------|----------------|---------------|
| Surface Composition | PVC            | ASTM D 751-06 |
| Finished Width      | 54" min.       | ASTM D 751-06 |
| Backing Composition | 100% Polyester | ASTM D 751-06 |
| Repeat              | None           | ASTM D 751-06 |
| Railroaded          | No             |               |
| Put-up              | 30 yards       |               |
| Cleaning Code       | W/S            |               |

| Performance                  | Values                           | Test Method                     |
|------------------------------|----------------------------------|---------------------------------|
| Grab Tensile                 | 110 lbs./in. × 110 lbs./in. min. | ASTM D 751-06                   |
| Trap Tear                    | 35 lbs./in. × 35 lbs./in. min.   | ASTM D 751-06                   |
| Seam Strength                | 35 lbs./in. × 35 lbs./in. min.   | ASTM D 751-06                   |
| Adhesion                     | 4 lbs./in. × 4 lbs./in. min.     | ASTM D 751-06                   |
| Stretch @ 15# (MD×CD)        | 7% × 30%                         | ASTM D 751-06                   |
| Flex Resistance              | 25,000 Cycles                    | ASTM D 2097-91                  |
| Blocking                     | No. 1 - Pass                     | FTMS 191A-TM5872                |
| Crock Resistance             | Dry - 4-5; Wet - 4-5             | AATCC 8-2016                    |
| Wyzenbeek Abrasion           | 100,000 cycles, #10 cotton duck  | ASTM D 4157-13                  |
| Colorfastness to Light       | 200 hours, Grade 4-5             | ASTM D 4329-05                  |
| Blue Dye Transfer Resistance | Dry - 4-5; Wet - 4               | Chrysler Method: LP-463KC-04-03 |

| Flammability                                   |      | Environmental                                        |
|------------------------------------------------|------|------------------------------------------------------|
| California Technical Bulletin 117-2013, Sec. 1 | Pass | 1. No anti-microbial additives                       |
| FMVSS/CMVSS #302                               | Pass | 2. Does not contain PFAS, PFOA                       |
| IMO A.652(16)8.2                               | Pass | 3. Prop 65 compliant                                 |
| NFPA 260                                       | Pass | 4. No chemical flame retardants, CA AB2998 compliant |
| U.F.A.C. Class I                               | Pass | 5. REACH and RoHS compliant – Phthalate free         |

**Suitable Applications** Contract, Healthcare, Hospitality, Residential

## Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

