




Bedrock



Bone



Brandy



Caramel



Cowhide



Dove




Driftwood




Dune



Dustbowl



Grey




Ivory




Mesquite



Pine



Slate



Tombstone



Tumbleweed

Construction	Values	Test Method
Surface Composition	100% PVC	ASTM D 751-06
Backing Composition	80% Polyester / 20%	ASTM D 751-06
Weight @ 54"	Cotton	ASTM D 751-06
Finished Width	26.5 oz./yd	ASTM D 751-06
Repeat	54" min.	
Railroaded	None	
Put-up	No	
Cleaning Code	30 yards W - Bleach Cleanable 10:1	

Performance	Values	Test Method
Grab Tensile	70 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Trap Tear	12 lbs./in. × 12 lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. × 65 lbs./in. min	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @15# (MD×CD)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-03(2010)
Blocking	No. 1 – Pass	FTMS 191A-TM5872
Crock Resistance	D-4; W-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-92
UV Stability	200 hours	ASTM D 4329-05

Flammability	Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass 1. Phthalate free
FMVSS/CMVSS #302	Pass 2. Lead free
NFPA 260	Pass 3. No FR chemicals
U.F.A.C. Class I	Pass 4. No antimicrobial chemicals

Suitable Applications Contract, Hospitality

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

