







PRODUCT SPECIFICATIONS

Construction	Values	Test Method	
Surface Composition	100% PVC		
Backing Composition	100% Polyester	ASTM D 751-89	
Finished Width	54" min.	ASTM D 751-89	
Repeat	None		
Railroaded	No		
Put-up	30 yards		
Cleaning Code	W		
Performance	Values	Test Method	
Grab Tensile	80 lbs./in. × 70 lbs./in. min.	ASTM D 5034-09	
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07	
Seam Strength	30 lbs./in. × 30 lbs./in. min.	ASTM D 1683-07A	
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-89	
Flex Resistance	30,000 cycles	ASTM D 2097-03	
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872	
Crock Resistance	Dry-5; Wet-5	AATCC 8-2013	
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-07	
UV Stability	500 hours	ASTM G 154	
Anti-bacterial	No growth	AATCC 147-2004	
Mildew Resistance	No growth	ASTM G-21	
Cold Crack (Roller Method)	-40°F - Pass	CFFA-6a	

FI	la	m	m	a	bi	lity
•	u	•••	•••	u	~ !	7

California Technical Bulletin 117-2013, Sec. 1	Pass	1. Does not contain PFAS, PFOA
IMO A.652(16)8.2	Pass	2. Prop 65 compliant
NFPA 260	Pass	3. No chemical flame retardants, CA AB2998 compliant
U.F.A.C. Class I	Pass	4. RoHS compliant – Phthalate free

Environmental

Suitable Applications Commercial

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



