





White



PRODUCT SPECIFICATIONS

| Construction | Values | Test Method |
|----------------------------------|-------------------------------------|----------------------|
| Surface Composition | 100% PVC | ASTM D 751-06 |
| Backing Composition | 80% Polyester / 20% Cotton | ASTM D 751-06 |
| Weight @ 54" | 26.5 oz./yd | ASTM D 751-06 |
| Finished Width | 54" min. | ASTM D 751-06 |
| Repeat | None | |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | W - Bleach Cleanable 10:1 | |
| Performance | Values | Test Method |
| Grab Tensile | 90 lbs./in.× 70 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 12 lbs./in. × 12 lbs./in. min. | ASTM D 751-06 |
| Seam Strength | 65 lbs./in. × 65 lbs./in. min | ASTM D 751-06 |
| Adhesion | 4 lbs./in. × 4 lbs./in. min. | ASTM D 751-06 |
| Stretch @15# (MD×CD) | 2% × 7% | ASTM D 751-06 |
| Flex Resistance | 25,000 cycles | ASTM D 2097-03(2010) |
| Blocking | No. 1 – Pass | FTMS 191A-TM5872 |
| Crock Resistance | D-4; W-4 | AATCC 8-2007 |
| Wyzenbeek Abrasion | 100,000 cycles, #10 cotton duck | ASTM D 4157-92 |
| UV Stability | 200 hours | ASTM D 4329-05 |
| Flammability | Environmento | al |
| California Technical Bulletin 11 | 7-2013, Sec. 1 Pass 1. Phthalate fr | ee |
| FMVSS/CMVSS #302 | Pass 2. Lead free | |

Suitable Applications Contract, Hospitality

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

Pass

Pass

3. No FR chemicals

4. No antimicrobial chemicals



NFPA 260

U.F.A.C. Class I

