




Bark



Black



Burgundy



Chestnut




Chocolate



Doe




Earth




Green Tea



Linen



Navy



Peacock



Red



White

| Construction | Values | Test Method |
|---------------------|----------------------------|--------------------|
| Surface Composition | 100% PVC | ASTM D 751-06 |
| Backing Composition | 80% Polyester / 20% Cotton | ASTM D 751-06 |
| Weight @ 54" | 26.5 oz./yd | ASTM D 751-06 |
| Finished Width | 54" min. | ASTM D 751-06 |
| Repeat | None | |
| Railroaded | No | |
| Put-up | 30 yards | |
| Cleaning Code | W - Bleach Cleanable 10:1 | |

| Performance | Values | Test Method |
|----------------------|---------------------------------|----------------------|
| Grab Tensile | 90 lbs./in. × 70 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 12 lbs./in. × 12 lbs./in. min. | ASTM D 751-06 |
| Seam Strength | 65 lbs./in. × 65 lbs./in. min | ASTM D 751-06 |
| Adhesion | 4 lbs./in. × 4 lbs./in. min. | ASTM D 751-06 |
| Stretch @15# (MD×CD) | 2% × 7% | ASTM D 751-06 |
| Flex Resistance | 25,000 cycles | ASTM D 2097-03(2010) |
| Blocking | No. 1 – Pass | FTMS 191A-TM5872 |
| Crock Resistance | D-4; W-4 | AATCC 8-2007 |
| Wyzenbeek Abrasion | 100,000 cycles, #10 cotton duck | ASTM D 4157-92 |
| UV Stability | 200 hours | ASTM D 4329-05 |

| Flammability | | Environmental |
|--|------|-------------------------------|
| California Technical Bulletin 117-2013, Sec. 1 | Pass | 1. Phthalate free |
| FMVSS/CMVSS #302 | Pass | 2. Lead free |
| NFPA 260 | Pass | 3. No FR chemicals |
| U.F.A.C. Class I | Pass | 4. No antimicrobial chemicals |

Suitable Applications Contract, Hospitality

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

