



Beige



Jesse James



Wild Bunch



Pecan



Dalton Gang



Coffee



Black



Graphite

Construction

Surface Composition
 Backing Composition
 Finished Width
 Repeat
 Railroaded
 Put-up
 Cleaning Code

Values

100% Polyurethane
 100% Polyester
 54" min.
 None
 No
 40 yards
 W

Test Method

ASTM D 751-89
 ASTM D 751-89

Performance

Grab Tensile
 Trap Tear
 Seam Strength
 Adhesion
 Stretch @ 15# (MD×CD)
 Flex Resistance
 Blocking
 Crock Resistance
 Wyzenbeek Abrasion
 Hydrolysis Resistance
 UV Stability

Minimum Values

150 lbs./in. × 100 lbs./in. min.
 20 lbs./in. × 20 lbs./in. min.
 70 lbs./in. × 60 lbs./in. min.
 4 lbs./in. × 4 lbs./in. min.
 2% × 9%
 25,000 Cycles
 No. 1 - Pass
 Wet-4; Dry-4
 100,000 cycles, #10 cotton duck
 3 weeks
 40 hours

Test Method

ASTM D 5034-09
 ASTM D 5587-07
 ASTM D 1683-11A
 ASTM D 751-89
 ASTM D 751-89
 ASTM D 2097-91
 Fed. Std. 191 A , 5872
 AATCC 8-2007
 ASTM D 4157-13
 ISO 1419-1995 E
 AATCC 16-2004

Flammability

California Technical Bulletin 117-2013, Sec. 1 Pass
 NFPA 260 Pass
 U.F.A.C. Class I Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. REACH, RoHS, and LEED compliant

Suitable Applications Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel.

