

OUTBACK











Jasper





Dove



Serene



Quartz



Fawn



Birch





Cement

Flax

Cameo



Silver



Rose



Wine



Aegean



Sky



Lagoon





PRODUCT SPECIFICATIONS

Construction	Values		Test Method
Surface Composition	100% Polyurethane		
Backing Composition	65% Polyester / 35% Cotton		ASTM D 751-06
Finished Width	54" min.		ASTM D 751-06
Repeat	None		
Railroaded	No		
Put-up	40 yards		
Cleaning Code	W		
Performance	Values		Test Method
Grab Tensile	80 lbs./in.× 70 lbs./in. min.		ASTM D 5034-09
Trap Tear	15 lbs./in. × 12 lbs./in. min.		ASTM D 2261-11
Seam Strength	60 lbs./in. × 60 lbs./in. min		ASTM D 1683-11a
Adhesion	4 lbs./in. × 4 lbs./in. min.		ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 7%		ASTM D 751-06
Flex Resistance	25,000 Cycles		ASTM D 2097-03(2010)
Blocking	No. 1 - Pass		FTMS 191A-TM5872
Crock Resistance	D-4; W-4		AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck		ASTM D 4157-92
Hydrolysis Resistance	7 weeks		ISO 1419: 1995 E
UV Stability	150 hours		ASTM D 4329-05
Flammability		Environmental	
California Technical Bulletin 117-2013, Sec. 1 Pas		1. No anti-microbial additives	
NFPA 260 Pas		2. Does not contain PFAS, PFOA	
U.F.A.C. Class I	Pass	Pass 3. Prop 65 compliant	
		4. No chemical flame retardants, CA AB2998 complian	
	5. REACH, RoHS, and LEED comp		and LEED compliant

Suitable Applications Commercial, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

