









PRODUCT SPECIFICATIONS

Construction	Values	Test Method		
Surface Composition	100% PVC			
Backing Composition	100% Polyester	ASTM D 751-89		
Finished Width	54" min.	ASTM D 751-89		
Repeat	None			
Railroaded	No			
Put-up	30 yards			
Cleaning Code	W			
Performance	Values	Test Method		
Grab Tensile	80 lbs./in. × 70 lbs./in. min.	ASTM D 5034-09		
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 5587-07		
Seam Strength	30 lbs./in. × 30 lbs./in. min.	ASTM D 1683-07A		
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-89		
Flex Resistance	30,000 cycles	ASTM D 2097-03		
Blocking	No. 1 - Pass	Fed. Std. 191 A , 5872		
Crock Resistance	Dry-5; Wet-5	AATCC 8-2013		
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-07		
UV Stability	500 hours	ASTM G 154		
Anti-bacterial	No growth	AATCC 147-2004		
Mildew Resistance	No growth	ASTM G-21		
Cold Crack (Roller Method)	-40°F - Pass	CFFA-6a		

ы		m	m	\sim	hı	litv
	ч			u	OI.	11 I V

Flammability		Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass	1. Does not contain PFAS, PFOA
IMO A.652(16)8.2	Pass	2. Prop 65 compliant
NFPA 260	Pass	3. No chemical flame retardants, CA AB2998 compliant
U.F.A.C. Class I	Pass	4. RoHS compliant – Phthalate free

Suitable Applications Commercial

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



