



Stone



Buckskin



Buff

Construction

Construction	Values
Surface Composition	100% Polyurethane
Backing Composition	100% Polyester
Finished Width	54" min.
Repeat	None
Railroaded	No
Put-up	30 yards
Cleaning Code	W

Test Method

ASTM D 751-06
ASTM D 751-06

Performance

Performance	Values	Test Method
Grab Tensile	80 lbs./in. × 70 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 12 lbs./in. min.	ASTM D 751-06
Seam Strength	60 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	20 cycles - Pass	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	40 hours	ASTM D 4329-05

Flammability

California Technical Bulletin 117-2013, Sec. 1	Pass
NFPA 260	Pass
U.F.A.C. Class I	Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. REACH, RoHS, and LEED compliant

Suitable Applications

 Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

