




Shark



Mineral



Gold



Walnut



Bronze



Chocolate



Ebony

Construction

Surface Composition
 Backing Composition
 Finished Width
 Repeat
 Railroaded
 Put-up
 Cleaning Code

Values

100% PVC
 70% Polyester / 30% Cotton
 54" min.
 None
 No
 30 yards
 W

Test Method

ASTM D 751-06
 ASTM D 751-06

Performance

Grab Tensile
 Trap Tear
 Seam Strength
 Adhesion
 Stretch @ 15# (MD×CD)
 Flex Resistance
 Blocking
 Crock Resistance
 Wyzenbeek Abrasion
 UV Stability

Values

85 lbs./in. × 90 lbs./in. min.
 15 lbs./in. × 15 lbs./in. min.
 65 lbs./in. × 65 lbs./in. min.
 4 lbs./in. × 4 lbs./in. min.
 2% × 9%
 25,000 Cycles
 No. 1 - Pass
 20 cycles - Pass
 100,000 cycles, #10 cotton duck
 40 hours (no color change)

Test Method

ASTM D 751-06
 ASTM D 2097-03(2010)
 FTMS 191A-TM5872
 AATCC 8-2007
 ASTM D 4157-92
 ASTM D 4329-05

Flammability

California Technical Bulletin 117-2013, Sec. 1 Pass
 MVSS-302 Pass
 NFPA 260 Pass
 U.F.A.C. Class I Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. RoHS compliant – Phthalate free

Suitable Applications Commercial

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

