MITCHELL™
COLLECTION

CROCK





Aztec


Bronze


Chamois


Matte Black


Mocha


Spruce


Topaz

MITCHELL COLLECTION

PRODUCT SPECIFICATIONS

CROCK

Construction	Values	Test Method
Surface Composition	100% PVC	
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	V: 10" / H: 10.75"	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance	Values	Test Method
Grab Tensile	85 lbs./in.× 90 lbs./in. min.	ASTM D 751-06
Trap Tear	15 lbs./in. × 15 lbs./in. min.	ASTM D 751-06
Seam Strength	65 lbs./in. × 65 lbs./in. min	ASTM D 751-06
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Wyzenbeek Abrasion	100,000 cycles, #8 cotton duck	ASTM D 4157-92
UV Stability	200 hours	ASTM D 4329-21
Crock Resistance	D-4; W-4	AATCC 8-2007
Stretch (MD×CD)	2% × 9% at 15 lbs.	ASTM D 751-06

Flammability

California Technical Bulletin 117-2013, Sec. 1	Pass
NFPA 260	Pass
U.F.A.C. Class I	Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. RoHS compliant – Phthalate free

Suitable Applications

Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. Stains can be removed with water-based household cleaners. Rinse with water after application of cleaners. Do not use chemical cleaners on this product.

MITCHELL Performance Faux Leathers | CLOROX HEALTHCARE

The Mitchell Group is a compatibility partner with Clorox Healthcare

The Mitchell Group
7040 N. Austin Avenue | Niles, IL 60714
847.647.7300 | mitchellfauxleathers.com