



Beige



Black



Coffee



Dalton Gang



Graphite



Jesse James



Pecan



Wild Bunch

Construction	Values	Test Method
Surface Composition	100% Polyurethane	
Backing Composition	100% Polyester	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Repeat	None	
Railroaded	No	
Put-up	40 yards	
Cleaning Code	W	

Performance	Values	Test Method
Grab Tensile	150 lbs./in. × 100 lbs./in. min.	ASTM D 5034-09
Trap Tear	20 lbs./in. × 20 lbs./in. min.	ASTM D 5587-07
Seam Strength	70 lbs./in. × 60 lbs./in. min.	ASTM D 1683-11A
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-89
Stretch @ 15# (MD×CD)	2% × 9%	ASTM D 751-89
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 – Pass	Fed. Std. 191 A, 5872
Crock Resistance	Wet – 4; Dry – 4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13
Hydrolysis Resistance	3 weeks	ISO 1419-1995 E
UV Stability	200 hours	ASTM D 4329-21

Flammability		Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass	1. No anti-microbial additives
NFPA 260	Pass	2. Does not contain PFAS, PFOA
U.F.A.C. Class I	Pass	3. Prop 65 compliant
		4. No chemical flame retardants, CA AB2998 compliant
		5. REACH, RoHS, and LEED compliant

Suitable Applications

Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. Stains can be removed with water-based household cleaners. Rinse with water after application of cleaners. Do not use chemical cleaners on this product.