




Beige



Black



Buckskin



Burgundy



Cafe



Chocolate




Dove




Gray



Honey



Hunter



Marine




Pecan



Stone



Wheat



White

Construction	Values	Test Method
Top Finish	Polyurethane	ASTM D 751-06
Surface Composition	PVC Foam	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	ASTM D 751-06
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	

Performance	Values	Test Method
Grab Tensile	80 lbs./in. × 60 lbs./in. min.	ASTM D 751-06
Trap Tear	18 lbs./in. × 18 lbs./in. min.	ASTM D 751-06
Seam Strength	35 lbs./in. × 35 lbs./in. min	ASTM D 751-06
Adhesion	3 lbs./in. × 3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 6%	ASTM D 751-06
Flex Resistance	25,000 Cycles	ASTM D 2097-91
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 cotton duck	ASTM D 4157-13
UV Stability	150 hours	ASTM D 4329-05
Hydrolysis Resistance	5 weeks	ISO 1419: 1995

Flammability	Environmental
California Technical Bulletin 117-2013, Sec. 1	Pass 1. No anti-microbial additives
FMVSS/CMVSS #302	Pass 2. Does not contain PFAS, PFOA
NFPA 260	Pass 3. Prop 65 compliant
U.F.A.C. Class I	Pass 4. No chemical flame retardants, CA AB2998 compliant
	5. REACH, RoHS, and LEED compliant

Suitable Applications Hospitality

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. Do not use chemical cleaners or disinfectants.