




Beaver




Buckskin



Buff



Burgundy



Cadet




Golden Brown



Goldenrod



Mink



Slate



Thatch

Construction	Values	Test Method
Surface Composition	100% PVC / Acrylic	ASTM D 751-06
Backing Composition	100% Polyester	ASTM D 751-06
Finished Width	54" min.	ASTM D 751-06
Repeat	None	
Railroaded	No	
Put-up	30 yards	
Cleaning Code	W	
Performance	Values	Test Method
Grab Tensile	80 lbs./in. × 80 lbs./in. min.	ASTM D 751-06
Tongue Tear	5.5 lbs./in. × 5.5 lbs./in. min.	ASTM D 751-06
Seam Strength	50 lbs./in. × 50 lbs./in. min.	ASTM D 751-06
Adhesion	3.3 lbs./in. × 3.3 lbs./in. min.	ASTM D 751-06
Stretch @ 15# (MD×CD)	2% × 7%	ASTM D 751-06
Flex Resistance	25,000 cycles	ASTM D 2097-03(2010)
Blocking	No. 1 - Pass	FTMS 191A-TM5872
Crock Resistance	Dry-4; Wet-4	AATCC 8-2007
Wyzenbeek Abrasion	100,000 cycles, #10 Cotton Duck	ASTM D 4157-92
UV Stability	200 hours	ASTM D 4329-05
Cold Crack (Roller Method)	-10°F - Pass	CFFA-6a

Flammability

California Technical Bulletin 117-2013, Sec. 1	Pass
FMVSS/CMVSS #302	Pass
NFPA 260	Pass
U.F.A.C. Class I	Pass

Environmental

1. Phthalate free
2. Lead free
3. No chemical flame retardants
4. No antimicrobial chemicals

Suitable Applications Commercial

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.