Arbor





Product Specifications

Arbor

Construction	Values	Test Method
Content	45% Polyurethane, 55% Recycled Polyester	
Backing Composition	100% Global Recycled Standard Polyester	ASTM D 751-06
Finished Width	54" min.	
Put-up	30 yards	ASTM D 751-06
Repeat	None	
Cleaning Code	W/S	
Performance	Values	Test Method
Adhesion	4 lbs./in. × 4 lbs./in. min.	ASTM D 751-06
Grab Tensile	80 lbs./in. × 120 lbs./in. min.	ASTM D 751-06
Trap Tear	45 lbs./in. × 50 lbs./in. min.	ASTM D 751-06
Seam Strength	45 lbs./in. × 110 lbs./in. min.	ASTM D 751-06
Stretch at 27# MD (warp) ×CD (fill)	6% × 24%	SAE J855, 2002
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - PASS	FTMS 191A-TM5872
Crock Resistance	Dry: 4.5 / Wet: 4.5	AATCC 8-2007
Wyzenbeek Abrasion	250,000 cycles, #10 Cotton Duck	ASTM D 4157-13
Hydrolysis Resistance	15 weeks	ISO 5423: 1992 E
UV Stability	200 hours	ASTM D 4329-05
Cold Crack (5# roller)	-40°F	CFFA-6A
Environmental		

No PVC, plasticizers, phthalates, formaldehyde, No halogenated FR Chemicals -

CAL AB2998 compliant stabilizers, or heavy metals

No persistent organic pollutants (POPs) Conflict mineral free No DMF or DMFA Prop 65 compliant

Zero chemical solvents LBC Red List compliant

No ozone-depleting chemicals CAL 01350 VOC compliant/low VOCs

No anti-microbial additives LEED - prequalified

Biocide, BPA, and TRIS Free RoHS, REACH compliant

Flammability

CA TB117-2013 Pass **NFPA 260 Pass** FMVSS/CMVSS #302 U.F.A.C. Class I Pass Pass

IMO A.652(16)8.2 **Pass**

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.





