Evergreen





Product Specifications

Evergreen

Construction	Values		Tool Motherd
Construction Content	Values 45% Polyurothono 55% Pocyclod Polyoctor		Test Method
	45% Polyurethane, 55% Recycled Polyester		ACTA 4 D 751 07
Backing Composition	100% Global Recycled Standard Polyester		ASTM D 751-06
Finished Width	54" min.		
Put-up	30 yards		ASTM D 751-06
Repeat	None		
Cleaning Code	W/S		
Performance	Values		Test Method
Adhesion	4 lbs./in. × 4 lbs./in. min.		ASTM D 751-06
Grab Tensile	80 lbs./in. × 120 lbs./in. min.		ASTM D 751-06
Trap Tear	45 lbs./in. × 50 lbs./in. min.		ASTM D 751-06
Seam Strength	45 lbs./in. × 110 lbs./in. min.		ASTM D 751-06
Stretch at 27# MD (warp) ×CD (fill)	6% × 24%		SAE J855, 2002
Flex Resistance	25,000 cycles		ASTM D 2097-91
Blocking	No. 1 - PASS		FTMS 191A-TM5872
Crock Resistance	Dry: 4.5 / Wet: 4.5		AATCC 8-2007
Wyzenbeek Abrasion	250,000 cycles, #10 Cotton Duck		ASTM D 4157-13
Hydrolysis Resistance	15 weeks		ISO 5423: 1992 E
UV Stability	200 hours		ASTM D 4329-05
Cold Crack (5# roller)	-40°F		CFFA-6A
Environmental			
No PVC, plasticizers, phthalates, formaldehyde, stabilizers, or heavy metals		No halogenated FR Chemic CAL AB2998 compliant	cals -
No persistent organic pollutants (POPs)		Conflict mineral free	
No DMF or DMFA		Prop 65 compliant	
Zero chemical solvents		LBC Red List compliant	
No ozone-depleting chemicals		CAL 01350 VOC compliant/low VOCs	
No anti-microbial additives		LEED - prequalified	

Flammability

CA TB117-2013 Pass NFPA 260 Pass FMVSS/CMVSS #302 Pass U.F.A.C. Class I Pass

REACH compliant

IMO A.652(16)8.2 Pass

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Biocide, BPA, and TRIS Free

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



