


Aegean



Apricot



Dark Sky




Fog



Harvest




India Ink




Inlet




Maya Blue



Midnight




Ocean



Pacific



Sea Mist



Sea Green



Shell




Silver Pine




Soot




Spa



Steel



Sumac



Sunshine

| Construction          | Values                                                                 | Test Method   |
|-----------------------|------------------------------------------------------------------------|---------------|
| Chemical Coating Face | 6% Silicone Protection and 94% Bio-Attributed PU build on Susterra PDO |               |
| Top Finish Protection | Hydro-Sil™ Finish                                                      |               |
| Backing Composition   | 100% GRS Transaction Certified Polyester                               | ASTM D 751-06 |
| Finished Width        | 54" min.                                                               |               |
| Put-up                | 30 yards                                                               | ASTM D 751-06 |
| Repeat                | None                                                                   |               |
| Cleaning Code         | W/S                                                                    |               |

| Performance                          | Values                           | Test Method      |
|--------------------------------------|----------------------------------|------------------|
| Adhesion                             | 4 lbs./in. × 4 lbs./in. min.     | ASTM D 751-06    |
| Grab Tensile                         | 100 lbs./in. × 180 lbs./in. min. | ASTM D 751-06    |
| Trap Tear                            | 25 lbs./in. × 25 lbs./in. min.   | ASTM D 751-06    |
| Seam Strength                        | 60 lbs./in. × 70 lbs./in. min.   | ASTM D 751-06    |
| Stretch at 27# MD (warp) × CD (fill) | 2% × 9%                          | SAE J855, 2002   |
| Flex Resistance                      | 25,000 cycles                    | ASTM D 2097-91   |
| Blocking                             | No. 1 - PASS                     | FTMS 191A-TM5872 |
| Crock Resistance                     | Dry Grade: 4.5 / Wet Grade: 4.5  | AATCC 8-2007     |
| Wyzenbeek Abrasion                   | 500,000 cycles, #10 Cotton Duck  | ASTM D 4157-13   |
| Hydrolysis Resistance                | 24 weeks                         | ISO 5423: 1992 E |
| UV Stability                         | 200 hours                        | ASTM D 4329-05   |
| Cold Crack (5# roller)               | -40°F                            | CFFA-6A          |

### Environmental

|                                                                              |                                                    |
|------------------------------------------------------------------------------|----------------------------------------------------|
| No PVC, plasticizers, phthalates, formaldehyde, stabilizers, or heavy metals | No halogenated FR Chemicals - CAL AB2998 compliant |
| No persistent organic pollutants (POPs)                                      | Conflict mineral free                              |
| No DMF or DMFA                                                               | Prop 65 compliant                                  |
| Zero chemical solvents                                                       | LBC Red List compliant                             |
| No ozone-depleting chemicals                                                 | CAL 01350 VOC compliant/low VOCs                   |
| No anti-microbial additives                                                  | LEED - prequalified                                |
| Biocide, BPA, and TRIS Free                                                  | RoHS, REACH compliant                              |

### Flammability

|                  |      |                  |      |
|------------------|------|------------------|------|
| CA TB117-2013    | Pass | NFPA 260         | Pass |
| FMVSS/CMVSS #302 | Pass | U.F.A.C. Class I | Pass |
| IMO A.652(16)8.2 | Pass |                  |      |

**Suitable Applications** Contract, Healthcare, Hospitality, Residential

### Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



The Mitchell Group is a compatibility partner with Clorox Healthcare



The Mitchell Group  
7040 N. Austin Avenue | Niles, IL 60714  
847.647.7300 | mitchellfauxleathers.com