


Snow




Ivory



Sunshine



Sea Foam




Haze



Hot Pink




Mist



New Sand



Penny




Celery




Cadet



Jelly Apple




Pewter




Goldenrod



Persimmon




Leaf



Peacock



Mulberry




Metal




Saddle



Brick



Stone



Ocean



Port



Ash




Chocolate




Malt



Khaki



Cobalt



Eggplant




Rain




Sage




Olive




Moss



Cloud



Ink




Black



Raisin



Espresso



Grotto

### Construction

Surface Composition  
Backing Composition  
Finished Width  
Repeat  
Railroaded  
Put-up  
Cleaning Code

### Values

100% Silicone  
100% Polyester  
54" min.  
None  
No  
25 yards  
W/S

### Test Method

ASTM D 751-06  
ASTM D 751-06

### Performance

Grab Tensile  
Trap Tear  
Seam Strength  
Adhesion  
Stretch @ 15# (MD×CD)  
Flex Resistance  
Blocking  
Crock Resistance  
Wyzenbeek Abrasion  
Colorfastness to Light  
Colorfastness to Water: Sea  
Colorfastness to Water: Chlorinated Pool  
Colorfastness to Perspiration  
Mildew Resistance  
Antibacterial Activity  
Antifungal Activity  
Blue Dye Transfer Resistance  
Biocompatibility - Vitro Cytotoxicity  
Biocompatibility - Irritation and Skin Sensitization  
Chemical Cleaner Resistance  
Cold Crack (Roller Method)

### Values

200 lbs./in. × 200 lbs./in. min.  
30 lbs./in. × 30 lbs./in. min.  
90 lbs./in. × 90 lbs./in. min.  
4 lbs./in. × 4 lbs./in. min.  
14% × 25%  
100,000 Cycles  
No. 1 - Pass  
Dry-5; Wet-5  
200,000 cycles, #10 Cotton Duck  
2,000 hours, Grade 4  
Shade-5; Staining-5  
4.8  
Acid-4.8; Alkaline-4.8  
Pass  
Pass  
Pass  
Dry-4; Wet-3-4  
Pass  
Pass  
Pass  
-40°F

### Test Method

ASTM D 751-06  
ASTM D 751-06  
ASTM D 751-06  
ASTM D 751-06  
ASTM D 751-06  
ASTM D 2097  
FTMS 191A-TM5872  
AATCC 8-2016  
ASTM D 4157-13  
ASTM D 4329-05  
AATCC 106-2013  
AATCC 162  
AATCC 15  
ASTM G-21  
AATCC 147  
AATCC 30, Test III  
LP-463KC-04-03  
ISO 10993-5-2009  
ISO 10993-10-2010  
ANSI BIFMA HCF 8.1-2017 Sections 6 & 7  
CFFA-6a

### Flammability

BS 5852 Crib 5  
California Technical Bulletin 117-2013, Sec. 1  
FMVSS/CMVSS #302  
IMO 2010-Part 8 Sec. 3.1 & 3.2  
NFPA 260 / NFPA 701  
U.F.A.C. Class I

Pass  
Pass  
Pass  
Pass  
Pass  
Pass

### Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. REACH, RoHS, and LEED compliant

### Suitable Applications Automotive, Contract, Healthcare, Hospitality

### Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

