





Aegean



Aqua



Charcoal



Cobalt



Dusk



Eggplant



Fog



Fox




Gray



Grotto



Marlin



Meadow



Mint



Moth



Moss



Ocean



Pigeon



Popsicle



Rain



Rust



Seafoam



Smoke



Spa



Steel



Steel



Sunshine

Construction	Values	Test Method
Surface Composition	100% Polycarbonate	
Backing Composition	50% Polyester / 50% Rayon	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Put-up	30 yards	
Repeat	None	
Cleaning Code	W/S	
Stain Resistant	Yes	

Performance	Values	Test Method
Adhesion	4 lbs. × 4 lbs.	ASTM D 751-89
Grab Tensile	120 lbs./in. × 100 lbs./in. min.	ASTM D 751-89
Trap Tear	15 lbs. × 15 lbs.	ASTM D 751-89
Seam Strength	40 lbs. × 40 lbs.	ASTM D 751-89
Stretch at 15# MD (warp) × CD (fill)	8% × 12%	ASTM D 5034-09
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 – PASS	FTMS 191A, 5872
Seam Slippage	25 lbs. × 25 lbs.	ASTM D 4034
Crock Resistance	Dry – 5; Wet – 5	AATCC 8-2001
Wyzenbeek Abrasion (#10 Cotton Duck)	300,000 cycles	ASTM D 4157-07
Hydrolysis Resistance	30 weeks	ISO 1419: 1995, Method C
Colorfastness to Light	1000 hours	AATCC 16-2004
Cold Crack (5# roller)	-20°F	CFFA-6A

Flammability

California Technical Bulletin 117-2013, Sec. 1	Pass
CMVSS #302	Pass
IMO A.652(16)8.2	Pass
NFPA 260	Pass
U.F.A.C. Class I	Pass

Environmental

1. No anti-microbial additives
2. Does not contain PFAS, PFOA
3. Prop 65 compliant
4. No chemical flame retardants, CA AB2998 compliant
5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

