



Aqua



Basil



Chestnut



Clay




Cork



Haze



Meadow



Metal



Nickel



Pearl



Pecan



Plaster



River



Sienna



Smoke



Tan



Taupe



Teal

| Construction | Values | Test Method |
|---------------------|---------------------------|---------------|
| Surface Composition | 100% Polycarbonate | |
| Backing Composition | 50% Rayon / 50% Polyester | ASTM D 751-06 |
| Finished Width | 54" min. | |
| Put-up | 30 yards | ASTM D 751-06 |
| Repeat | None | |
| Cleaning Code | WS | |
| Railroaded | No | |

| Performance | Values | Test Method |
|--------------------------------------|----------------------------------|--------------------------|
| Adhesion | 4 lbs./in. × 4 lbs./in. min. | ASTM D 751-06 |
| Grab Tensile | 120 lbs./in. × 100 lbs./in. min. | ASTM D 751-06 |
| Trap Tear | 20 lbs./in. × 15 lbs./in. min. | ASTM D 751-06 |
| Seam Strength | 60 lbs./in. × 60 lbs./in. min. | ASTM D 751-06 |
| Stretch at 15# MD (warp) ×CD (fill) | 4% × 18% | SAE J855, 2002 |
| Flex Resistance | 25,000 cycles | ASTM D 2097-91 |
| Blocking | No. 1 – PASS | FTMS 191A-TM5872 |
| Crock Resistance | Dry – 5; Wet – 5 | AATCC 8-2007 |
| Wyzenbeek Abrasion (#10 Cotton Duck) | 300,000 cycles | ASTM D 4157-13 |
| Hydrolysis Resistance | 30 weeks | ISO 1419: 1995, Method C |
| Colorfastness to Light | 1000 hours | ASTM D 4329-05 |
| Blue Dye Transfer Resistance | Dry – 4-5; Wet – 4-5 | LP-463KC-04-03 |
| Cold Crack (5# roller) | -20°F | CFFA-6A |

| Flammability | Environmental | |
|------------------------------------------------|---------------|------------------------------------------------------|
| California Technical Bulletin 117-2013, Sec. 1 | Pass | 1. No anti-microbial additives |
| FMVSS/CMVSS #302 | Pass | 2. Does not contain PFAS, PFOA |
| IMO A.652(16)8.2 | Pass | 3. Prop 65 compliant |
| NFPA 260 | Pass | 4. No chemical flame retardants, CA AB2998 compliant |
| U.F.A.C. Class I | Pass | 5. REACH, RoHS, and LEED compliant |

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

