









Product Specifications



Construction	Values	Test Method
Surface Composition	100% Polycarbonate	
Backing Composition	50% Polyester, 50% Rayon	ASTM D 751-89
Finished Width	54" min.	ASTM D 751-89
Put-up	30 yards	
Repeat	None	
Cleaning Code	W/S	
Stain Resistant	Yes	
Performance	Values	Test Method
Adhesion	4 lbs. × 4 lbs.	ASTM D 751-89
Breaking Strength	80 lbs. × 60 lbs.	ASTM D 751-89
Trap Tear	15 lbs. × 15 lbs.	ASTM D 751-89
Seam Strength	40 lbs. × 40 lbs.	ASTM D 751-89
Stretch at 15# MD (warp) ×CD (fill)	8% × 12%	ASTM D 5034-09
Flex Resistance	25,000 cycles	ASTM D 2097-91
Blocking	No. 1 - PASS	FTMS 191A, 5872
Seam Slippage	25 lbs. × 25 lbs.	ASTM D 4034
Crock Resistance	D-5; W-5	AATCC 8-2001
Wyzenbeek Abrasion	300,000 cycles, #10 Cotton Duck	ASTM D 4157-07
Mildew Resistance	Pass - No growth	ASTM G-21
Anti-Bacterial	Pass - No growth	AATCC 147-2004
	10 weeks	ASTM D 3690-02
Hydrolysis Resistance	15 weeks	ISO 5423: 1992 (E)
Colorfastness to Light	1000 hours	AATCC 16-2004
Cold Crack (5# roller)	-20°F	CFFA-6A
Flammability	Environmental	

Flammability	Enviro

California Technical Bulletin 117-2013, Sec. 1	Pass	 No anti-microbial additives
CMVSS #302	Pass	2. Does not contain PFAS, PFOA
IMO A.652(16)8.2	Pass	3. Prop 65 compliant
NFPA 260	Pass	4. No chemical flame retardants, CA AB2998 compliant
U.F.A.C. Class I	Pass	5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



