







Charcoal



| Construction | Values | Test Method | |
|--------------------------------------|----------------------------------|------------------------------------|--|
| urface Composition | 100% Polycarbonate | | |
| inished Width | 54" min. | | |
| sacking Composition | 50% Rayon, 50% Polyester | ASTM D 751-06 | |
| Put-up | 30 yards | ASTM D 751-06a | |
| Repeat | None | | |
| Cleaning Code | WS | | |
| Railroaded | No | | |
| erformance | Values | Test Method | |
| Adhesion | 4 lbs./in. × 4 lbs./in. min. | ASTM D 751-06 | |
| Grab Tensile | 150 lbs./in. × 130 lbs./in. min. | ASTM D 751-06 | |
| rap Tear | 20 lbs./in. × 15 lbs./in. min. | ASTM D 751-06 | |
| eam Strength | 85 lbs./in. × 80 lbs./in. min. | ASTM D 751-06 | |
| tretch at 15# MD (warp) ×CD (fill) | 4% × 16% | SAE J855, 2002 | |
| lex Resistance | 25,000 cycles | ASTM D 2097-91 | |
| Blocking | No. 1 - PASS | FTMS 191A-TM5872 | |
| Crock Resistance | Wet-5; Dry-5 | AATCC 8-2007 | |
| Vyzenbeek Abrasion (#10 Cotton Duck) | 500,000 cycles | ASTM D 4157-13 | |
| łydrolysis Resistance | 15 weeks | ASTM D 3690-02; ISO 1419: 1995 (E) | |
| Colorfastness to Light | 1000 hours | ASTM D 4329-05 | |
| llue Dye Transfer Resistance | Dry-4-5; Wet-4-5 | LP-463KC-04-03 | |
| Cold Crack (5# roller) | -20°F | CFFA-6A | |

| Flammability | / |
|--------------|----------|
| Hammadilli | <i>(</i> |

| California Technical Bulletin 117-2013, Sec. 1 | Pass | 1. No anti-microbial additives |
|--|------|--|
| FMVSS/CMVSS #302 | Pass | 2. Does not contain PFAS, PFOA |
| IMO A.652(16)8.2 | Pass | 3. Prop 65 compliant |
| NFPA 260 | Pass | 4. No chemical flame retardants, CA AB2998 compliant |
| U.F.A.C. Class I | Pass | 5. REACH, RoHS, and LEED compliant |

Environmental

Suitable Applications Contract, Healthcare, Hospitality, Residential

Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.



