


# Bubble





Midnight

## **Product Specifications**

#### Construction

| Surface Composition |
|---------------------|
| Backing Composition |
| Finished Width      |
| Repeat              |
| Railroaded          |
| Put-up              |
| Cleaning Code       |

#### Performance

| renonnunce            |
|-----------------------|
| Grab Tensile          |
| Trap Tear             |
| Seam Strength         |
| Adhesion              |
| Stretch @ 15# (MD×CD) |
| Flex Resistance       |
| Blocking              |
| Crock Resistance      |
|                       |

## Wyzenbeek Abrasion Hydrolysis Resistance UV Stability

| Blue Dye Transfer Resistance |
|------------------------------|
| Anti-Bacterial               |
| Mildew Resistance            |
| Cold Crack (#5 roller)       |

#### Flammability

California Technical Bulletin 117-2013, Sec. 1 FMVSS/CMVSS #302 IMO A.652(16)8.2 NFPA 260 U.F.A.C. Class I

### Values

| 100% Polyurethane |
|-------------------|
| 100% Polyester    |
| 54" min.          |
| None              |
| No                |
| 30 yards          |
| W/S               |

## Values

| VUIUES                          |
|---------------------------------|
| 80 lbs./in.× 80 lbs./in.        |
| 15 lbs./in. × 15 lbs./in.       |
| 40 lbs./in. x 35 lbs./in.       |
| 4 lbs./in. × 4 lbs./in.         |
| 2% × 6%                         |
| 25,000 cycles                   |
| No. 1 Pass                      |
| Dry-4; Wet-4                    |
| 300,000 cycles, #10 Cotton Duck |
| 5 weeks                         |
| 7 weeks                         |
| 150 hours (Grade 4)             |
| Dry-4-5; Wet-4-5                |
| Pass                            |
| Pass                            |
| -20°F                           |

### **Test Method**

ASTM D 751-06 ASTM D 751-06

## **Test Method**

| ASTM D 751-06          |
|------------------------|
| ASTM D 751-06          |
| ASTM D 2097-91         |
| Fed. Std. 191 A , 5872 |
| AATCC 8-2007           |
| ASTM D 4157-07         |
| ASTM D 3690-02         |
| ISO 1419: 1995         |
| ASTM D 4329-05         |
| LP-463KC-04-03         |
| AATCC 147-2004         |
| ASTM G-21              |
| CFFA-6A                |
|                        |

#### Environmental

1. No anti-microbial additives

- 2. Does not contain PFAS, PFOA
- 3. Prop 65 compliant
- 4. No chemical flame retardants, CA AB2998 compliant
- 5. REACH, RoHS, and LEED compliant

Suitable Applications Contract, Healthcare, Hospitality, Residential

### **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

Pass

Pass

Pass

Pass

Pass

