




Copper



Crystal



Midnight




Mint



Mushroom



Pearl



Smoke

### Construction

| Construction        | Values            | Test Method   |
|---------------------|-------------------|---------------|
| Surface Composition | 100% Polyurethane |               |
| Backing Composition | 100% Polyester    | ASTM D 751-06 |
| Finished Width      | 54" min.          | ASTM D 751-06 |
| Repeat              | None              |               |
| Railroaded          | No                |               |
| Put-up              | 30 yards          |               |
| Cleaning Code       | W/S               |               |

### Performance

| Performance                          | Values                    | Test Method           |
|--------------------------------------|---------------------------|-----------------------|
| Grab Tensile                         | 80 lbs./in. × 80 lbs./in. | ASTM D 751-06         |
| Trap Tear                            | 15 lbs./in. × 15 lbs./in. | ASTM D 751-06         |
| Seam Strength                        | 40 lbs./in. × 35 lbs./in. | ASTM D 751-06         |
| Adhesion                             | 4 lbs./in. × 4 lbs./in.   | ASTM D 751-06         |
| Stretch @ 15# (MD×CD)                | 2% × 6%                   | ASTM D 751-06         |
| Flex Resistance                      | 25,000 cycles             | ASTM D 2097-91        |
| Blocking                             | No. 1 Pass                | Fed. Std. 191 A, 5872 |
| Crock Resistance                     | Dry - 4; Wet - 4          | AATCC 8-2007          |
| Wyzenbeek Abrasion (#10 Cotton Duck) | 300,000 cycles            | ASTM D 4157-07        |
| Hydrolysis Resistance                | 19 weeks                  | ISO 1419: 1995 E      |
| UV Stability                         | 150 hours (Grade 4)       | ASTM D 4329-05        |
| Blue Dye Transfer Resistance         | Dry - 4-5; Wet - 4-5      | LP-463KC-04-03        |
| Cold Crack (#5 roller)               | -20°F                     | CFFA-6A               |

### Flammability

|                                                |      |
|------------------------------------------------|------|
| California Technical Bulletin 117-2013, Sec. 1 | Pass |
| FMVSS/CMVSS #302                               | Pass |
| IMO A.652(16)8.2                               | Pass |
| NFPA 260                                       | Pass |
| U.F.A.C. Class I                               | Pass |

### Environmental

|                                                      |
|------------------------------------------------------|
| 1. No anti-microbial additives                       |
| 2. Does not contain PFAS, PFOA                       |
| 3. Prop 65 compliant                                 |
| 4. No chemical flame retardants, CA AB2998 compliant |
| 5. REACH, RoHS, and LEED compliant                   |

### Suitable Applications

Contract, Healthcare, Hospitality, Residential

### Cleaning and Disinfecting

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

