





Construction	Values		Test Method
Surface Composition	100% Polyure	ethane	
Backing Composition	100% Polyester		ASTM D 751-89
Finished Width	54" min.		ASTM D 751-89
Repeat	None		
Railroaded	No		
Put-up	30 yards		
Cleaning Code	W/S		
Performance	Values		Test Method
Grab Tensile	50 lbs./in.× 50 lbs./in.		ASTM D 5034-09
Trap Tear	15 lbs./in. × 15 lbs./in.		ASTM D 5587-07
Seam Strength	40 lbs./in. × 40 lbs./in.		ASTM D 1683-07A
Adhesion	4 lbs./in. × 4 lbs./in		ASTM D 751-89
Stretch @ 15# MD (warp) ×CD (fill)	2% ×8%		ASTM D 751-89
Flex Resistance	25,000 cycles		ASTM D 2097-91
Blocking	No. 1 - Pass		Fed. Std. 191 A, 5872
Crock Resistance	Dry - 4; Wet - 4		AATCC 8-2013
Wyzenbeek Abrasion (#10 Cotton Duck)	300,000 cycles		ASTM D 4157-10
Hydrolysis Resistance	24 weeks		ISO 1419: 1995 E
UV Stability	150 hours		ASTM D 4329-05
Blue Dye Transfer Resistance	Dry - 4-5; Wet - 4-5		LP-463KC-04-03
Cold Crack (#5 roller)	-20°F		CFFA-6A
Flammability		Environmental	
California Technical Bulletin 117-2013, Sec. 1 Pass		1. No anti-microbial additives	
IMO A.652(16)8.2 Pass		2. Does not contain PFAS, PFOA	

Suitable Applications Contract, Healthcare, Hospitality, Residential

## **Cleaning and Disinfecting**

Remove ordinary dirt and smudges with mild soap and water. A 10:1 ratio of water to bleach solution may be used as a disinfectant. Rinse the surface with clean water after disinfecting. Dry with a soft, lint-free cloth or towel. We recommend that you use Clorox Healthcare and Clorox Pro products to disinfect Mitchell products in commercial settings.

Pass

Pass

3. Prop 65 compliant

4. No chemical flame retardants, CA AB2998 compliant

5. REACH, RoHS, and LEED compliant



**NFPA 260** 

U.F.A.C. Class I

